

Natural Wood Boat Varnish

Product properties

Natural Wood Boat Varnish is a urethane alkyd varnish specially for treatment on wood. Provides a robust, weather and salt water resistant surface. Natural Wood Boat Varnish is available semi-gloss or glossy.

Product use

Indoors and outdoors for varnishing wood.

Substrate

Must be clean, dry, solid and suitable for surface treatment.

Treatment

Clean previously painted surfaces with Natural Wood Wood Cleaner.

Previously varnished surfaces must be sanded matt.

Wipe with a hard-wrung cloth.

Untreated wood, outdoors, can be primed with Natural Wood Boat Varnish diluted with 10-20% white spirit.

The best result achieved by three treatments before use.

Application

Brush.

After priming, apply 3 coats of undiluted Natural Wood Boat Varnish.

Apply wet-on-wet, and finish by brushing in the same direction.

Condensation during drying / curing must not form.

Always apply test treatments to check and accept the adhesion and results.

Expected result

Colorless and glossy surface which appears saturated and uniform in gloss and finish.

The durability of the surface depends on the wood quality, structure, application and exposure.

Please note!

Protect freshly painted surface from adverse weather conditions.

Take appropriate measures against the effects of moisture and rainfall on freshly varnished surfaces.

The surface achieves maximum robustness when fully cured.

Environmental information

Remove as much paint from tools as possible before cleaning.

Bring remains of fluent paint to the local recycling centre.

Minimize your paint waste by pre-estimating how much paint you need.

Keep the leftover paint for future use so you can effectively reduce the environmental impact.



Storage: Cool, frost free and tightly closed

Protection equipment: Painting: eye protection, gloves. Sanding: respiratory protection.

Technical Data

Gloss	Gloss;Semi Gloss
Density (kgs/l)	0.90
Solids Weight %	46
Solids Vol. %	40
Nominal spreading rate (m ² /ltr.)	10
Min. working temp. during application and drying/curing	Min. +5°C
Humidity	Max. humidity 80 % RH.
Drying time at 20° C, 60 % RH (Hours)	4
Recoatable at 20° C, 60 % RH (Hours)	24
Fully cured at 20° C, 60 % RH (Days)	28
Dilution	Do not dilute
Cleaning of Tools etc.	Brush Cleaner

Current TDS Version

May 2024

Replaces TDS Version

March 2024